

Deep Cycle AGM Batteries

C12-165XDA (12V / 165Ah)




Century AGM Deep Cycle Batteries are the ultimate in deep cycle battery performance, designed to provide longer life and dependable deep cycling capability in the harshest of operating conditions and environments.


The Century Deep Cycle AGM range utilises Absorbed Glass Mat (AGM) technology which absorbs the liquid electrolyte within highly porous glass fibre mat separators. This eliminates loose electrolyte whilst the sealed maintenance free design prevents acid leaks and the need for on-going maintenance. Extra strong grid designs, superior active paste material and robust internal components ensure lower self discharge, superior vibration resistance, longer cycle life and improved recharge capabilities.


Century Deep Cycle AGM batteries are ideal for use in applications where fast recharge, and superior deep cycle capabilities are required, such as recreational vehicles and accessories, dual battery systems, golf carts, electric wheel chairs, mobility scooters and marine systems.


Product Specification					
Cells	6	Weight	Approx. 50.0 kg		
Voltage	12	Max. Discharge Current	1650 A (5 sec)		
Capacity	pacity 165Ah@20hr-rate to 1.75V per cell @ 25°C Internal Resistance				
	Discharge:-20°C~60°C	Terminal	M8 Insert		
Operating Temperature Range	Charge: 0°C~50°C Storage: -20°C~60°C	Container Material	A.B.S. (UL94-HB)		
Normal Operating Temperature Range	25°C ± 5°C	Recommended Max. Charging - Current Limit	48A		
Float Charging Voltage	13.6 to 13.8 VDC/unit Average at 25°C	Equalisation & Cycle Service	14.6 to 14.8VDC/unit Average at 25°C		
Self Discharge	Century AGM batteries can be stored for more than 6 months at 25°C. Self-discharge rate less than 3% per month at 25°C. Please charge batteries before using.	Note: Warranty void if mounted u The C12-165DA battery cannot be			

Unit: mm **Dimension:** 530 (L) x 209 (W) x 214 (H) x 219 (TH)









	Discharge Current VS Discharge Voltage								
	Final Discharge Voltage V/Cell	1.75V	1.70V	1.60V					
	Discharge Current	(A) ≤0.2C	0.2C< (A) <1.0C	(A) ≥1.0C					

Charge the batteries at least once a month every six months, if they are stored at 25°C


Charging Metho	d
Constant Voltage	-0.2Cx2h+2.4~2.45V/Cellx24h,Max.Current 0.3CA


Constant Current Discharge Characteristics: A (25°C) F.V/Time 5MIN 10MIN 15MIN 30MIN 1HR 2HR 3HR 4HR 5HR 8HR 10HR **20HR** 9.60V 551.5 395.2 287.5 176.6 99.84 57.00 40.09 33.18 26.11 19.08 16.13 8.532 10.0V 536.7 376.0 281.6 173.7 99.38 56.57 39.94 33.02 25.96 18.92 15.98 8.377 32.87 10.2V 505.8 362.7 277.2 172.2 98.46 56.14 39.63 25.80 18.77 15.82 8.221 10.5V 454.2 334.7 263.9 167.9 97.54 55.71 39.48 32.56 25.50 18.61 15.67 8.066 10.8V 409.9 243.3 54.71 31.80 25.04 18.30 15.51 7.911 305.2 160.5 95.23 38.40 11.1V 356.8 272.8 218.2 150.4 90.47 52.28 36.71 30.26 23.96 17.53 15.05 7.446


onstant F	Power D	Discharg	ge Char	acteristi	ics: W (25°C)						
F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
9.60V	5252	3841	2828	1993	1142	655.7	462.6	383.4	302.3	221.4	181.4	95.82
40.01/	EAAE	2660	2760	4060	4426	CE2 4	4647	202 5	200.4	220 5	470 E	0.4.90


1.4/111116	JIVIIII	TOWING	LOMILIA	JUMINA	11111	21111	JIIIX	7111	JIIIX	OTTIC	101111	201111
9.60V	5252	3841	2828	1993	1142	655.7	462.6	383.4	302.3	221.4	181.4	95.82
10.0V	5145	3668	2769	1969	1136	653.1	461.7	382.5	300.4	220.5	179.5	94.89
10.2V	4857	3546	2732	1945	1128	647.1	459.0	380.6	299.5	218.6	178.6	93.96
10.5V	4373	3277	2605	1901	1117	641.1	456.2	377.9	296.8	216.8	176.7	93.03
10.8V	3934	2975	2393	1815	1089	631.7	445.1	367.7	292.1	212.1	174.9	92.10
11.1V	3396	2642	2137	1700	1032	602.5	423.0	350.2	277.4	204.7	169.3	88.37

All mentioned values are average values.











Battery Disposal This battery is 98% recyclable. Help create a cleaner planet, return your used battery to the original place of purchase or your nearest CenturyYuasa approved Battery Recycling Centre.

